Durometer Hardness Conversion Table

The hardness values listed below are approximate and should only be used as a durometer selection guide. Physical tests by the end user are the only accurate way of ensuring proper product selection.

Durometer Type Scale

	Α	В	C	D	0	00
	100	85	77	5 8		
	95	81	70	46		
-	90	76	59	39	1	
	85	71	52	33		
	80	66	47	29	84	98
	75	62	42	25	79	97
Ü	70	56	37	22	75	95
١	65	51	32	19	72	94
	60	47	28	16	69	93
	55	42	24	14	65	91
	5 0	37	20	12	61	90
	45	32	17	10	57	88
	40	27	14	8	53	86
	35	22	12	7	48	83
	30	17	9	6	42	80
	25	12			35	76
	20	6			28	70
	15				21	62
	10				14	55
	5				8	45

H A R D N E S

U E

Note: Information herein is based on laboratory test data, which is believed to be reliable. However Kodiak Corporation has no control over the end application of these materials. Therefore, we cannot guarantee that the same results as described herein will be obtained

Note: It is recommended that each user conduct his / her own tests to determine adaptability of these materials to his / her particular application.